



NOTES:

1. MANHOLE BASES FOR MAINS 15" AND LARGER SHALL BE COATED **PER SM-07**.
2. LOWEST POINT ON SHELF SHALL BE EVEN WITH TOP OF PIPE.
3. CAST IN PLACE MANHOLE BASES CAST WITH 560-C-3250 SHALL BE CURED A MINIMUM OF THREE DAYS PRIOR TO STACKING MANHOLE. BASES CAST WITH 660-CW-4000 (WITHOUT CALCIUM CHLORIDE (CC)) OR WITH 560-C-3250 TREATED WITH A MINIMUM OF 2% CC SOLUTION IN ACCORDANCE WITH 201-1 SHALL BE CURED A MINIMUM OF 24 HOURS. THESE CURING REQUIREMENTS APPLY TO MANHOLES WITH A MAXIMUM HEIGHT OF 25'. SHORTER CURING TIMES, DEEPER INSTALLATIONS, AND ALTERNATE CONCRETE MIX DESIGNS REQUIRE ENGINEER'S PRIOR APPROVAL.
4. CONCRETE SPECIFIED BY ALTERNATE CLASS OR OTHERWISE CONTAINING FLY ASH IS NOT ALLOWED FOR USE IN CAST IN PLACE MANHOLES.
5. CONCRETE MIX DESIGNS CONTAINING ACCELERATING ADMIXTURES OTHER THAN CC REQUIRE A BREAK HISTORY AND ENGINEER'S APPROVAL.

REVISION	BY	APPROVED	DATE	CITY OF SAN DIEGO – STANDARD DRAWING	RECOMMENDED BY THE CITY OF SAN DIEGO STANDARDS COMMITTEE
ORIGINAL*	KA	J. NAGELVOORT	01/12		SEWER MANHOLE BASE
UPDATED	HM	J. NAGELVOORT	02/16	COORDINATOR R.C.E. 81047 DATE	
REDRAFTED	CD	J. NAGELVOORT	09/18		
UPDATED	RC	R. AMEN	05/26		
				DRAWING NUMBER	SDS-120